



# BTL™-12 String Reinforced

**Black/White**

**LOW TEMPERATURE - HYDROCARBON STABLE**

<b>DESCRIPTION</b>	BLACK 12 X 12 COUNT PER INCH	
<b>FABRICATION &amp; WAREHOUSE</b>	PRINEVILLE, OREGON	
<b>THICKNESS</b>	12 MILS (+/-10%)	ASTM D 5199
<b>PEEL</b>	76.2 oz	ASTM D 1876
<b>1" Elongation at Break MD/TD</b>	643.8% / 750.0 %	
<b>1" Load at Yield MD/TD</b>	24.8 lbf / 25.8 lbf	ASTM D 882
<b>1" Load at Break MD/PSI</b>	28 lbf / 2742.5 psi	ASTM D 882
<b>1" Load at Break TD/PSI</b>	27.7 lbf / 2713.3 psi	ASTM D 882
<b>3" Load at Yield MD/PSI</b>	76.8 lbf / 118.3 lbf	ASTM D 882
<b>3" Load at Break MD/PSI</b>	74.6 lbf / 2436.7 psi	ASTM D 882
<b>3" Load at Break TD/PSI</b>	75.2 lbf / 2456.9 psi	ASTM D 882
<b>3" Elongation at Break MD/TD</b>	611.3% / 759.3%	
<b>Tongue Tear</b>	20.8 lbf / 25.4lbf	ASTM D 2261
<b>Trapezoidal Tear</b>	30.2 lbf / 43.7 lbf	ASTM D 4533
<b>PPT Resistance MD/TD</b>	36.7 lbf / 26.8 lbf	ASTM D 2582

ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES. AVAILABLE ON REQUEST.  
03/2015