



BTL™-16 BW

Single Scrim RPE

LOW TEMPERATURE - HYDROCARBON STABLE

FABRICATION & WAREHOUSE	PRINEVILLE, OREGON	
WEIGHT	7.5 OZ./SQ.YD. (+/-5%)	ASTM D1910
THICKNESS	16 MIL (+/-10%)	
COATING THICKNESS	2 MIL EACH (+/-5%)	
TENSILE STRENGTH (GRAB METHOD)	Warp 210 LBS. Weft 190 LBS.	ASTM D 775
TEAR STRENGTH (TONGUE METHOD)	Warp 60 LBS. Weft 60 LBS.	ASTM D 775
BURSTING STRENGTH (MULLEN)	375 PSI	ASTM D3786
HYDROSTATIC RESISTANCE	97 PSI	ASTM D775
PUNCTURE RESISTANCE	113 LBS.	ASTM D4833
LOW TEMPERATURE COLD CRACK	-22 ° F	ASTM D2136
UV RESISTANCE	>90% STRENGTH RETAINED AFTER 2000 HRS.	ASTM G-154

ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES. AVAILABLE ON REQUEST.



Certified to
NSF/ANSI 61-G & 372